



**BUREAU
VERITAS**

TEST REPORT

2M95 Kisten einlegen

Technical Report: (6611)165-1060

June 28, 2011

Date Received: June 14, 2011

Page 1 of 3

Sample Description:

Sample(s) received is/are stated to be:

1. HD BAG, TRANSPARENT, (650+450)*650
2. HD BAG, BLUE, (650+450)*650
3. LD BAG, TRANSPARENT, 200*300

Color:	/	Style No(s):	/
Order No.:	/	PO No.:	/
Model No.:	/	Batch No.:	/
Age Grade:	/	Product End Use:	/
Vendor:	/	Retest No.:	/
Manufacturer:	/	Supplier Reference:	/
Buyer:	/	Country of Origin:	/
Test Period:	June 14, 2011 to June 28, 2011	Country of Destination:	/

SUMMARY OF TEST RESULTS

TEST REQUESTED	CONCLUSION
Overall Migration Test for Plastic Materials in Contact with Foodstuffs— Commission Regulation (EU) No. 10/2011 and Its Amendments	PASS

REMARK

If there are questions or concerns on this report, please contact the following persons:

General enquiry and invoicing

Ms. Summer Ji

Technical enquiry

Mr. Simon Zhang / Mr. Matthias Chan

BUREAU VERITAS
CONSUMER PRODUCTS SERVICES DIVISION

PREPARED BY : Summer

Simon
Matthias Chan
DIRECTOR

RW/2011




Technical Report:

(6611)165-1060

June 28, 2011

Page 2 of 3

Photo of the Submitted Sample





Technical Report:

(6611)165-1060

June 28, 2011

Page 3 of 3

TEST RESULT

Sample Description Assigned by Laboratory:

Test Item	Description
1	Transparent plastic (HD bag) (650+450)*650
2	Blue plastic (HD bag) (650+450)*650
3	Transparent plastic (LD bag) (200*300)

Overall Migration Test for Plastic Materials in Contact with Foodstuffs – Commission Regulation (EU) No. 10/2011 and Its Amendments

Test Condition: 3% Acetic acid: 5 °C, 10 days
95% Ethanol: 5 °C, 10 days

Simulant Used	Unit	Result	Maximum Allowable Limit	Analytical Tolerance
		1		
3% Acetic acid	mg/dm ²	<5	10	+2
95% Ethanol	mg/dm ²	<5	10	+3
Conclusion	-	PASS	-	-

Test Condition: 3% Acetic acid: 5 °C, 10 days
95% Ethanol: 5 °C, 10 days

Simulant Used	Unit	Result	Maximum Allowable Limit	Analytical Tolerance
		2		
3% Acetic acid	mg/dm ²	<5	10	+2
95% Ethanol	mg/dm ²	<5	10	+3
Conclusion	-	PASS	-	-

Test Condition: 3% Acetic acid: 5 °C, 10 days
95% Ethanol: 5 °C, 10 days

Simulant Used	Unit	Result	Maximum Allowable Limit	Analytical Tolerance
		3		
3% Acetic acid	mg/dm ²	<5	10	+2
95% Ethanol	mg/dm ²	<5	10	+3
Conclusion	-	PASS	-	-

Note: "<" = less than
mg/dm² = milligram per square decimeter

Method: EN 1186-1: 2002, EN 1186-2: 2002, EN 1186-3: 2002 and EN 1186-14: 2002.

Remark: 1) Selected test was specified by client.
2) The test condition and simulant used were specified by client.

END